

EAST Search History

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	553	"thermosetting resin" and "dielectric constant" and epoxy and nitrogen	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2006/03/29 09:16
L2	133	L1 and prepreg and laminate	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2006/03/29 09:15
L3	58	L2 and GHz	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2006/03/29 09:15
L4	72	"thermosetting resin" and "dielectric constant" and epoxy and "nitrogen atom"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2006/03/29 09:17
L5	5	L4 and GHz and prepreg and laminate	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2006/03/29 09:17

EAST Search History

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	2610	"thermosetting resin" and styrene and "maleic anhydride"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2006/03/29 11:00
L2	219	"thermosetting resin" and styrene and "maleic anhydride" and "dielectric constant"	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2006/03/29 11:01
L3	62	"thermosetting resin" and styrene and "maleic anhydride" and "dielectric constant" and prepreg	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2006/03/29 11:02

EAST Search History

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	154	"thermosetting resin" and (N-phenylmaleimide or N-hydroxyphenylmaleimide)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2006/03/29 14:15
L2	28	"thermosetting resin" and (N-phenylmaleimide or N-hydroxyphenylmaleimide) and prepreg	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB	OR	OFF	2006/03/29 14:15